

# LEXAN™ MARGARD™ MRX SHEET

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ MARGARD™ MRX sheet is a transparent UV and mar resistant glazing material for flat applications only. The intrinsic properties of LEXAN polycarbonate combined with its dual hard coated surface provide: high impact strength and forced entry protection, graffiti resistance, enhanced chemical resistance, good all weather performance, unique ten (10) year warranty against breakage and five (5) year limited warranty against yellowing, loss of light transmission and coating failure. Typical applications can be sound-barriers, separations screens and flat glazing systems needing impact resistance combined with chemical and abrasion resistance.

### TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
<b>PHYSICAL</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.20
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
<b>MECHANICAL</b>			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
Taber haze - 500 cycles, 500 gram, CS-10F	ASTM D1044	%	<10
<b>THERMAL</b>			
Vicat softening temperature, rate B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75-2	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 <sup>-5</sup>
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
<b>ELECTRICAL</b>			
Volume resistivity	IEC 60093	Ohm.cm	>10 <sup>15</sup>
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
<b>OPTICAL</b>			
Light transmission 3 mm	ASTM D1003	%	91
Light transmission 4 mm	ASTM D1003	%	90
Light transmission 5 mm	ASTM D1003	%	89
Light transmission 6 mm	ASTM D1003	%	89
Light transmission 8 mm	ASTM D1003	%	87
Light transmission 9.5 mm	ASTM D1003	%	86
Light transmission 12 mm	ASTM D1003	%	84
Light transmission 15 mm	ASTM D1003	%	82

◆ Some of the property values have been derived from LEXAN™ resin data for the material used to produce this sheet product.  
 ™ Trademark of SABIC.

## FLAT APPLICATIONS

Due to its mar-resistant coating, LEXAN™ MARGARD™ MRX sheet cannot be formed. Cold-line bending may result in cracks in the sheet and coating. The sheet is intended for flat applications only.

## CHEMICAL RESISTANCE

LEXAN MARGARD MRX sheet has high resistance at the coated side to many chemicals. In applications where it will come into contact with aggressive chemicals, specific (application related) testing of the material is strongly recommended.

## PRODUCT AVAILABILITY #)

GAUGE (MM)	WIDTH (MM)	LENGTH (MM)	COLOR
3.00	2000	3000	112
4.00	2000	3000	112
6.00	2000	3000	112
8.00	2000	3000	112
9.50	2000	3000	112
12.0	2000	3000	112
15.0	2000	3000	112

# From 3.00mm up to and including 15.00mm, other dimensions upon request and are subject to minimum order quantities.

## INSTALLATION

For some applications the ripple orientation may play an important role while installing the LEXAN MARGARD MRX sheet.

## ASSEMBLING

Parts made from LEXAN MARGARD MRX sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these techniques can cause environmental stress cracking, please ensure that you have carried out tests regarding its suitability for your applications or end use.

## CLEANING

- Never scrape the sheet with squeegees, razorblades or other sharp instruments.
- Do not clean LEXAN MARGARD MRX sheet products under sunny and/or hot environments.
- For removal of paints, marker pen inks, lipstick and graffiti etc. on the coated side, we recommend to use Butyl Cellusolve and products mentioned in the LEXAN solid sheet processing manual. Do not use abrasive or alkaline cleaners.
- To remove labels, stickers etc. the use of kerosene, naphtha or white spirit is generally effective.
- After having cleaned the LEXAN MARGARD MRX sheet a final wash should be made, using a mild soap solution and finishing with a thorough rinsing with cold water.

## CONTACT US:

### SABIC CORPORATE HQ

PO Box 5101  
Riyadh 11422  
Saudi Arabia  
T +966 (0) 1 225 8000  
F +966 (0) 1 225 9000  
E info@sabic.com

### AMERICAS

SABIC  
Functional Forms  
2500 CityWest Boulevard  
Suite 100  
Houston, TX 77042  
USA  
Toll-free (800) 323 3783  
F (888) 443 2033

### EUROPE

SABIC  
Functional Forms  
Plasticslaan 1  
4612 PX  
Bergen op Zoom  
The Netherlands  
T +31 (0)164 293684  
F +31 (0)164 293272

### PACIFIC

SABIC  
Functional Forms  
2550 Xiupu Road  
Pudong  
201319 Shanghai  
China  
T +86 21 3222 4500  
F +86 21 6289 8998

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES (SELLER) ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.  
© Copyright 2021. All rights reserved.

<sup>1</sup> Any brands, products or services of other companies referenced in this document are the trademarks.

